

Product Definition for SkidLyte™

Description

SkidLyte™ is an anti-skid aggregate made of ground polymer granules that are classified into 3 grades ranging from 175 - 650 microns and are available in 4 colors, which include Clear, Blue, Red, Yellow. **SkidLyte™** is also available in an “after glow” color that would be perfectly suited for illuminating emergency exits or dark areas.

These non-dispersing pigments can be easily incorporated into Seamless Floors, Road Striping, Safety Markings and Paint & Coatings. Typical applications are in paint, floor coatings, gel coat systems, and spray-ups



Typical Properties - (non-specified)

Chemical Analysis

Alyl Polycarbonate

Binder & Colorant

Moisture

Physical

Bleed – Aqueous Grades

Water (@ 200 degrees F)

Mineral Oil (@ 150 degrees F)

Bleed – Resin Grades

Water (@ ambient temp.)

Mineral Oil (@ 450 degrees F)

Specific Gravity

Loose Bulk Density

Percentage by Weight

99 – 100

1

>1

Result

Pass

Fail

Fail

Pass

1.35

40

Approximate Particle Sizes:

Grade	U.S. Mesh
650	- 10 / +30
325	-30 / +80
175	-80

The information contained herein is believed to be reliable, but is presented without guaranty, warranty, or responsibility of any kind, express or implied, as to its accuracy, its suitability for particular use, or the results to be obtained. Statements or suggestions concerning possible use of our products are made without representation or warranty that any such use is free of patent infringement, and are not recommendations to infringe any patent. Because of the variations in methods, conditions, and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Elpis Technologies shall not be liable for and the customer assumes all-risk and liability of any use or handling of any material beyond the direct control of Elpis Technologies. SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OR MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. The user should not assume that all safety measures are indicated herein or that other measures may not be required. Before handling, using, or processing any material, always read its material safety data sheet.
04/01/2008